

# Santoprene™ 101-64

## Thermoplastic Vulcanizate

Product Description	Key Features
A soft, black, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable.	<ul style="list-style-type: none"> <li>• UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component.</li> <li>• Recommended for applications requiring excellent flex fatigue resistance.</li> <li>• Excellent ozone resistance.</li> <li>• EU Directive 2002/95/EC (RoHS) compliant.</li> </ul>

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>• Africa &amp; Middle East</li> <li>• Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>• Europe</li> <li>• Latin America</li> </ul>	<ul style="list-style-type: none"> <li>• North America</li> <li>• South America</li> </ul>
Applications	<ul style="list-style-type: none"> <li>• Automotive - Air Induction System Ducts</li> <li>• Automotive - Boots and Bellows for Steering and Suspension</li> <li>• Automotive - Plugs, Bumpers, Grommets, Clips</li> <li>• Automotive - Seals and Gaskets</li> <li>• Automotive - Weather Seals</li> <li>• Consumer - Electronics</li> <li>• Consumer - Floor Care</li> <li>• Industrial - Seals and Gaskets</li> <li>• Tubing</li> </ul>		
Uses	<ul style="list-style-type: none"> <li>• Appliance Components</li> <li>• Automotive Applications</li> <li>• Automotive Under the Hood</li> </ul>	<ul style="list-style-type: none"> <li>• Consumer Applications</li> <li>• Diaphragms</li> <li>• Electrical Parts</li> </ul>	<ul style="list-style-type: none"> <li>• Gaskets</li> <li>• Seals</li> <li>• Tubing</li> </ul>
Agency Ratings	<ul style="list-style-type: none"> <li>• EU 2003/11/EC</li> </ul>	<ul style="list-style-type: none"> <li>• UL QMFZ2</li> </ul>	<ul style="list-style-type: none"> <li>• UL QMFZ8</li> </ul>
RoHS Compliance	<ul style="list-style-type: none"> <li>• RoHS Compliant</li> </ul>		
Automotive Specifications	<ul style="list-style-type: none"> <li>• CHRYSLER MS-AR100 BGN</li> <li>• DELPHI 8565</li> <li>• DELPHI DX300003</li> </ul>	<ul style="list-style-type: none"> <li>• FORD WSD-M2D379-A1</li> <li>• GM GMP.E/P.002</li> <li>• TRW TMS-P-10,365</li> </ul>	<ul style="list-style-type: none"> <li>• VALEO VMS-8618</li> </ul>
Color	<ul style="list-style-type: none"> <li>• Black</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>• Pellets</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>• Blow Molding</li> <li>• Coextrusion</li> <li>• Extrusion</li> </ul>	<ul style="list-style-type: none"> <li>• Extrusion Blow Molding</li> <li>• Injection Blow Molding</li> <li>• Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>• Multi Injection Molding</li> <li>• Profile Extrusion</li> <li>• Sheet Extrusion</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>• 11/27/2007</li> </ul>		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Specific Gravity	0.970	0.970	ASTM D792
Density	0.970 g/cm <sup>3</sup>	0.970 g/cm <sup>3</sup>	ISO 1183

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore A, 15 sec, 73°F (23°C), 0.0787 in (2.00 mm)	69	69	

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ISO 37

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.

**ExxonMobil Chemical Santoprene™ 101-64  
Thermoplastic Vulcanizate**

<b>Elastomers</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Based On</b>
Tensile Strength at Break - Across Flow (73°F (23°C))	1020 psi	7.00 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	1020 psi	7.00 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	450 %	450 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	450 %	450 %	ISO 37
Tear Strength - Across Flow (73°F (23°C), Die C)	131 lbf/in	23.0 kN/m	ASTM D624
Tear Strength - Across Flow 73°F (23°C), Method Bb, Angle (Nicked)	130 lbf/in	23 kN/m	ISO 34-1
Compression Set 158°F (70°C), 22.0 hr, Type 1	18 %	18 %	ASTM D395B
257°F (125°C), 70.0 hr, Type 1	44 %	44 %	
Compression Set 158°F (70°C), 22.0 hr, Type A	18 %	18 %	ISO 815
257°F (125°C), 70.0 hr, Type A	44 %	44 %	
<b>Thermal</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Based On</b>
Brittleness Temperature	-76 °F	-60 °C	ASTM D746
Brittleness Temperature	-76 °F	-60 °C	ISO 812
<b>Electrical</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Based On</b>
Volume Resistivity 73°F (23°C), 0.0800 in (2.03 mm)	1.0E+16 ohm-cm	1.0E+16 ohm-cm	ASTM D257
73°F (23°C), 0.130 in (3.30 mm)	5.0E+15 ohm-cm	5.0E+15 ohm-cm	
Dielectric Strength 0.0800 in (2.03 mm)	730 V/mil	29 kV/mm	ASTM D149
73°F (23°C), 0.130 in (3.30 mm)	620 V/mil	25 kV/mm	
Dielectric Constant 73°F (23°C), 0.0780 in (1.98 mm)	2.50	2.50	ASTM D150
Dielectric Constant 73°F (23°C), 0.0780 in (1.98 mm)	2.50	2.50	IEC 60250
<b>Injection</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	
Drying Temperature	180 °F	82.2 °C	
Drying Time	3.0 hr	3.0 hr	
Suggested Max Moisture	0.080 %	0.080 %	
Suggested Max Regrind	20 %	20 %	
Rear Temperature	350 °F	177 °C	
Middle Temperature	360 °F	182 °C	
Front Temperature	360 °F	182 °C	
Nozzle Temperature	370 to 430 °F	188 to 221 °C	
Processing (Melt) Temp	380 to 450 °F	193 to 232 °C	
Mold Temperature	50.0 to 125 °F	10.0 to 51.7 °C	
Injection Rate	Fast	Fast	
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa	
Screw Speed	100 to 200 rpm	100 to 200 rpm	
Clamp Tonnage	3.0 to 5.0 tons/in <sup>2</sup>	41 to 69 MPa	

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.

## ExxonMobil Chemical Santoprene™ 101-64 Thermoplastic Vulcanizate

Injection	Typical Value (English)	Typical Value (SI)
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm
Screw L/D Ratio	16.0:1.0 to 20.0:1.0	16.0:1.0 to 20.0:1.0
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	2.0:1.0 to 2.5:1.0
Vent Depth	0.0010 in	0.025 mm

### Injection Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

Extrusion	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82.2 °C
Drying Time	3.0 hr	3.0 hr
Melt Temperature	385 °F	196 °C
Die Temperature	390 °F	199 °C
Back Pressure	725 to 2900 psi	5.00 to 20.0 MPa

### Extrusion Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Extrusion Guide.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-12 %	-12 %	ASTM D573
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-12 %	-12 %	ISO 188
Change in Ultimate Elongation in Air 302°F (150°C), 168 hr	6.0 %	6.0 %	ASTM D573
Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr	6.0 %	6.0 %	ISO 188
Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr	2.0	2.0	ASTM D573
Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr	2.0	2.0	ISO 188
Continuous Upper Temperature Resistance	275 °F	135 °C	SAE J2236

### Additional Information

Values are for injection molded plaques, fan-gated, 102.0 mm x 152.0 mm x 2.0 mm (4.000" x 6.000" x 0.080").  
Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.  
Compression set at 25% deflection.

### Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

### Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Material Safety Data Sheet, Injection Molding Guide, Extrusion Guide and Blow Molding Guide.

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.

# ExxonMobil Chemical Santoprene™ 101-64 Thermoplastic Vulcanizate

## Notes

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

---

Worldwide and the Americas  
ExxonMobil Chemical Company  
13501 Katy Freeway  
Houston, TX 77079-1398  
USA  
1-281-870-6050

Asia Pacific  
ExxonMobil Chemical Singapore Pte. Ltd.  
1 HarbourFront Place  
#06-00 HarbourFront Tower One  
Singapore 098633  
66-2163-8444

Europe, Middle East and Africa  
ExxonMobil Chemical Europe  
Hermeslaan 2  
1831 Machelen, Belgium  
420-239-016-274

[contact us](#)

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.