



Zytel®

nylon resin

Zytel® 70G33L NC010 Glass Reinforced Nylon Resin

Zytel® 70G33L NC010 is a 33% glass reinforced general purpose PA 66 resin.

Property	Test Method	Units	Value	
			DAM	50%RH
Mechanical				
Tensile Strength	ASTM D 638	MPa (kpsi)		
-40C (-40F)			214 (31.0)	207 (30.0)
23C (73F)			186 (27.0)	124 (18.0)
77C (170F)			110 (16.0)	86 (12.5)
Stress at Break	ISO 527-1/-2	MPa (kpsi)	193 (28.0)	126 (18.3)
Elongation at Break	ASTM D 638	%	3	4
Strain at Break	ISO 527-1/-2	%	3.2	5
Tensile Modulus	ISO 527-1/-2	MPa (kpsi)	10500 (1520)	7000 (1015)
Shear Strength	ASTM D 732	MPa (kpsi)	86 (12.5)	
Poisson's Ratio			0.39	
Flexural Modulus	ASTM D 790	MPa (kpsi)	8965 (1300)	6205 (900)
Flexural Modulus	ISO 178	MPa (kpsi)	9100 (1320)	6205 (900)
Flexural Strength	ASTM D 790	MPa (kpsi)	262 (38.0)	
Deformation Under Load	ASTM D 621	%		
50C (122F), 13.8MPa (2000psi)			0.8	
Izod Impact	ASTM D 256	J/m (ft lb/in)	117 (2.2)	133 (2.5)
Notched Izod Impact	ISO 180/1A	kJ/m2		
-40C (-40F)			9	10
-30C (-22F)				10
23C (73F)		11	15	
Unnotched Izod Impact	ISO 180/1U	kJ/m2		
-30C (-22F)				70
23C (73F)				90
Notched Charpy Impact	ISO 179/1eA	kJ/m2		
-40C (-40F)			9	10
-30C (-22F)			10	10
23C (73F)			12	16
Unnotched Charpy Impact	ISO 179/1eU	kJ/m2		
-30C (-22F)			85	70
23C (73F)			95	100

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Zytel® is a DuPont registered trademark.

990209/991020

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Product Information

Zytel® 70G33L NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Thermal				
Heat Deflection Temperature 0.45MPa (66psi)	ASTM D 648	°C (°F)	261 (502)	
1.8MPa (264psi)			249 (480)	
Deflection Temperature 1.80MPa	ISO 75-1/-2	°C (°F)	254 (489)	
CLTE, Parallel -40 - 23C (-40 - 73F)	ASTM E 831	E-4/C (E-4/F)	0.24 (0.13)	
23 - 55C (73 - 130F)			0.18 (0.10)	
55 - 160C (130 - 320F)			0.13 (0.07)	
CLTE, Normal -40 - 23C (-40 - 73F)	ASTM E 831	E-4/C (E-4/F)	0.65 (0.36)	
23 - 55C (73 - 130F)			0.83 (0.46)	
55 - 160C (130 - 320F)			1.37 (0.76)	
Melting Point	ASTM D 3418	°C (°F)	262 (504)	
Melting Temperature	ISO 3146C	°C (°F)	263 (505)	
Electrical				
Surface Resistivity 1mm	IEC 60093	ohm	1E12	
Relative Permittivity 1E2 Hz, 1mm	IEC 60250		4.2	
1E6 Hz, 1mm			3.9	
Volume Resistivity	ASTM D 257	ohm cm	1 E15	
Volume Resistivity 1mm	IEC 60093	ohm cm	1E15	
Dielectric Strength, Short Time	ASTM D 149	kV/mm (V/mil)	20.9 (530)	
Dielectric Strength, Step by Step	ASTM D 149	kV/mm (V/mil)	17.3 (440)	
Dielectric Constant 1E3 Hz	ASTM D 150		4.5	
1E6 Hz			3.7	
Dissipation Factor 1E3 Hz	ASTM D 150		0.02	
1E6 Hz			0.02	
Dissipation Factor 1E2 Hz, 1mm	IEC 60250	E-4	90	
1E6 Hz, 1mm			150	
Arc Resistance	ASTM D 495	s	135	
CTI	UL 746A	V	>600	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Zytel® is a DuPont registered trademark.

990209/991020

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/enggpolymer

Product Information

Zytel® 70G33L NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Flammability				
Flammability Classification	UL94			
0.71mm			HB	
1.5mm			HB	
3.0mm			HB	
Limited Oxygen Index	ISO 4589	%	24	
High Voltage Arc Tracking Rate	UL 746A	mm/min (in/min)	32.2 (1.27)	
Hot Wire Ignition	UL 746A	s	9	
Temperature Index				
RTI, Electrical	UL 746B	°C		
0.71mm			105	
1.5mm			120	
3.0mm			120	
RTI, Mechanical with Impact	UL 746B	°C		
0.71mm			65	
1.5mm			105	
3.0mm			105	
RTI, Mechanical without Impact	UL 746B	°C		
0.71mm			105	
1.5mm			120	
3.0mm			120	
Other				
Specific Gravity	ASTM D 792		1.38	
Density	ISO 1183	kg/m3 (g/cm3)	1390 (1.39)	
Hardness, Rockwell Scale M	ASTM D 785		101	
Taber Abrasion CS-17 Wheel, 1kg, 1000 cycles	ASTM D 1044	mg		14
Humidity Absorption Equilibrium 50%RH	ISO 62, Similar to	%	1.7	
Water Absorption Immersion 24h	ASTM D 570	%	0.7	
Saturation			5.4	
Water Absorption Saturation, immersed	ISO 62, Similar to	%	5.7	
Mold Shrinkage Flow, 3.2mm (0.126in)		%	0.2	
Molding Shrinkage Normal, 2.0mm	ISO 294-4	%	1.1	
Parallel, 2.0mm			0.4	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Zytel® is a DuPont registered trademark.

990209/991020

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/enggpolymer

Product Information

Zytel® 70G33L NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Processing				
Melt Temperature Range		°C (°F)	290-305 (550-580)	
Mold Temperature Range		°C (°F)	65-120 (150-250)	
Processing Moisture Content		%	<0.20	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Zytel® is a DuPont registered trademark.

990209/991020

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/enggpolymer